

Abstract

Table 1

Experimental details

Crystal data	
Chemical formula	La ₂ Ni ₂
M_r	395.24
Crystal system, space group	Orthorhombic, <i>Cmcm</i>
Temperature (K)	300
a, b, c (Å)	3.9213 (5), 10.7970 (13), 4.3833 (6)
V (Å ³)	185.58 (4)
Z	2
Radiation type	Mo $K\alpha$
μ (mm ⁻¹)	32.27
Crystal size (mm)	0.08 × 0.04 × 0.03
Data collection	
Diffractometer	Bruker D8 Venture Photon 100 CMOS
Absorption correction	Multi-scan (<i>SADABS</i> ; Krause et al., 2015)
T_{\min}, T_{\max}	0.393, 0.746
No. of measured, independent and observed [$I > 2\sigma(I)$] reflections	3183, 138, 130
R_{int}	0.061
$(\sin \theta/\lambda)_{\text{max}}$ (Å ⁻¹)	0.649
Refinement	
$R[F^2 > 2\sigma(F^2)], wR(F^2), S$	0.025, 0.061, 1.28
No. of reflections	138
No. of parameters	9
$\Delta\rho_{\text{max}}, \Delta\rho_{\text{min}}$ (e Å ⁻³)	1.75, -0.90

Computer programs: *SHELXL2019/1* (Sheldrick, 2019).**References**

NOT FOUND

full crystallographic data

Computing details

Program(s) used to refine structure: *SHELXL2019/1* (Sheldrick, 2019).

(LaNi_a)

Crystal data

La ₂ Ni ₂	$D_x = 7.073 \text{ Mg m}^{-3}$
$M_r = 395.24$	Mo $K\alpha$ radiation, $\lambda = 0.71073 \text{ \AA}$
Orthorhombic, <i>Cmcm</i>	Cell parameters from 2113 reflections
$a = 3.9213 (5) \text{ \AA}$	$\theta = 3.8\text{--}27.5^\circ$
$b = 10.7970 (13) \text{ \AA}$	$\mu = 32.27 \text{ mm}^{-1}$
$c = 4.3833 (6) \text{ \AA}$	$T = 300 \text{ K}$
$V = 185.58 (4) \text{ \AA}^3$	Lump, gray
$Z = 2$	$0.08 \times 0.04 \times 0.03 \text{ mm}$
$F(000) = 340$	

Data collection

Bruker D8 Venture Photon 100 CMOS diffractometer	138 independent reflections
phi and ω scans	130 reflections with $I > 2\sigma(I)$
Absorption correction: multi-scan (<i>SADABS</i> ; Krause et al., 2015)	$R_{\text{int}} = 0.061$
$T_{\text{min}} = 0.393$, $T_{\text{max}} = 0.746$	$\theta_{\text{max}} = 27.5^\circ$, $\theta_{\text{min}} = 3.8^\circ$
3183 measured reflections	$h = -5 \rightarrow 5$
	$k = -14 \rightarrow 14$
	$l = -5 \rightarrow 5$

Refinement

Refinement on F^2	0 restraints
Least-squares matrix: full	$w = 1/[\sigma^2(F_o^2) + (0.0317P)^2 + 1.7562P]$
$R[F^2 > 2\sigma(F^2)] = 0.025$	where $P = (F_o^2 + 2F_c^2)/3$
$wR(F^2) = 0.061$	$(\Delta/\sigma)_{\text{max}} < 0.001$
$S = 1.28$	$\Delta\rho_{\text{max}} = 1.75 \text{ e \AA}^{-3}$
138 reflections	$\Delta\rho_{\text{min}} = -0.90 \text{ e \AA}^{-3}$
9 parameters	

Special details

Geometry. All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2) for (LaNi_a)

	<i>x</i>	<i>y</i>	<i>z</i>	$U_{\text{iso}}^*/U_{\text{eq}}$
La1	0.000000	0.13738 (6)	0.250000	0.0177 (3)
Ni1	0.000000	0.42941 (16)	0.250000	0.0227 (4)

Atomic displacement parameters (\AA^2) for (LaNi₂a)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
La1	0.0189 (4)	0.0169 (4)	0.0174 (4)	0.000	0.000	0.000
Ni1	0.0251 (9)	0.0249 (9)	0.0182 (9)	0.000	0.000	0.000

Geometric parameters (\AA , $^\circ$) for (LaNi₂a)

La1—Ni1 ⁱ	2.9810 (14)	La1—La1 ^{vii}	3.6884 (11)
La1—Ni1 ⁱⁱ	2.9810 (14)	La1—La1 ^{viii}	3.6884 (11)
La1—Ni1 ⁱⁱⁱ	3.0278 (5)	La1—La1 ^{iv}	3.8159 (9)
La1—Ni1 ^{iv}	3.0278 (5)	La1—La1 ^v	3.8159 (9)
La1—Ni1 ^v	3.0278 (5)	La1—La1 ^{vi}	3.8159 (9)
La1—Ni1 ^{vi}	3.0278 (5)	Ni1—Ni1 ^{ix}	2.670 (2)
La1—Ni1	3.1530 (18)	Ni1—Ni1 ^x	2.670 (2)
Ni1 ⁱ —La1—Ni1 ⁱⁱ	82.25 (5)	Ni1—La1—La1 ^v	50.410 (16)
Ni1 ⁱ —La1—Ni1 ⁱⁱⁱ	52.75 (4)	La1 ^{vii} —La1—La1 ^v	148.633 (12)
Ni1 ⁱⁱ —La1—Ni1 ⁱⁱⁱ	104.27 (2)	La1 ^{viii} —La1—La1 ^v	99.864 (10)
Ni1 ⁱ —La1—Ni1 ^{iv}	104.27 (2)	La1 ^{iv} —La1—La1 ^v	61.835 (17)
Ni1 ⁱⁱ —La1—Ni1 ^{iv}	52.75 (4)	Ni1 ⁱ —La1—La1 ^{vi}	144.884 (9)
Ni1 ⁱⁱⁱ —La1—Ni1 ^{iv}	152.44 (7)	Ni1 ⁱⁱ —La1—La1 ^{vi}	98.17 (2)
Ni1 ⁱ —La1—Ni1 ^v	52.75 (4)	Ni1 ⁱⁱⁱ —La1—La1 ^{vi}	93.94 (2)
Ni1 ⁱⁱ —La1—Ni1 ^v	104.27 (2)	Ni1 ^{iv} —La1—La1 ^{vi}	103.58 (2)
Ni1 ⁱⁱⁱ —La1—Ni1 ^v	92.74 (2)	Ni1 ^v —La1—La1 ^{vi}	154.19 (4)
Ni1 ^{iv} —La1—Ni1 ^v	80.714 (18)	Ni1 ^{vi} —La1—La1 ^{vi}	53.37 (3)
Ni1 ⁱ —La1—Ni1 ^{vi}	104.27 (2)	Ni1—La1—La1 ^{vi}	50.410 (16)
Ni1 ⁱⁱ —La1—Ni1 ^{vi}	52.75 (4)	La1 ^{vii} —La1—La1 ^{vi}	99.864 (10)
Ni1 ⁱⁱⁱ —La1—Ni1 ^{vi}	80.714 (18)	La1 ^{viii} —La1—La1 ^{vi}	148.633 (12)
Ni1 ^{iv} —La1—Ni1 ^{vi}	92.74 (2)	La1 ^{iv} —La1—La1 ^{vi}	70.11 (2)
Ni1 ^v —La1—Ni1 ^{vi}	152.44 (7)	La1 ^v —La1—La1 ^{vi}	100.82 (3)
Ni1 ⁱ —La1—Ni1	138.87 (2)	Ni1 ^{ix} —Ni1—Ni1 ^x	110.36 (12)
Ni1 ⁱⁱ —La1—Ni1	138.87 (2)	Ni1 ^{ix} —Ni1—La1 ^{xi}	64.53 (5)
Ni1 ⁱⁱⁱ —La1—Ni1	103.78 (4)	Ni1 ^x —Ni1—La1 ^{xi}	64.53 (5)
Ni1 ^{iv} —La1—Ni1	103.78 (4)	Ni1 ^{ix} —Ni1—La1 ^{xii}	64.53 (5)
Ni1 ^v —La1—Ni1	103.78 (4)	Ni1 ^x —Ni1—La1 ^{xii}	64.53 (5)
Ni1 ^{vi} —La1—Ni1	103.78 (4)	La1 ^{xi} —Ni1—La1 ^{xii}	82.25 (5)
Ni1 ⁱ —La1—La1 ^{vii}	52.709 (19)	Ni1 ^{ix} —Ni1—La1 ⁱⁱⁱ	136.91 (4)
Ni1 ⁱⁱ —La1—La1 ^{vii}	52.709 (18)	Ni1 ^x —Ni1—La1 ⁱⁱⁱ	62.73 (2)
Ni1 ⁱⁱⁱ —La1—La1 ^{vii}	51.56 (3)	La1 ^{xi} —Ni1—La1 ⁱⁱⁱ	127.25 (4)
Ni1 ^{iv} —La1—La1 ^{vii}	103.80 (4)	La1 ^{xii} —Ni1—La1 ⁱⁱⁱ	75.73 (2)
Ni1 ^v —La1—La1 ^{vii}	103.80 (4)	Ni1 ^{ix} —Ni1—La1 ^{iv}	62.73 (2)
Ni1 ^{vi} —La1—La1 ^{vii}	51.56 (3)	Ni1 ^x —Ni1—La1 ^{iv}	136.91 (4)
Ni1—La1—La1 ^{vii}	143.544 (13)	La1 ^{xi} —Ni1—La1 ^{iv}	75.73 (2)
Ni1 ⁱ —La1—La1 ^{viii}	52.709 (18)	La1 ^{xii} —Ni1—La1 ^{iv}	127.25 (4)
Ni1 ⁱⁱ —La1—La1 ^{viii}	52.709 (18)	La1 ⁱⁱⁱ —Ni1—La1 ^{iv}	152.44 (7)
Ni1 ⁱⁱⁱ —La1—La1 ^{viii}	103.80 (4)	Ni1 ^{ix} —Ni1—La1 ^{vi}	136.91 (4)
Ni1 ^{iv} —La1—La1 ^{viii}	51.56 (3)	Ni1 ^x —Ni1—La1 ^{vi}	62.73 (2)
Ni1 ^v —La1—La1 ^{viii}	51.56 (3)	La1 ^{xi} —Ni1—La1 ^{vi}	75.73 (2)
Ni1 ^{vi} —La1—La1 ^{viii}	103.80 (4)	La1 ^{xii} —Ni1—La1 ^{vi}	127.25 (4)
Ni1—La1—La1 ^{viii}	143.544 (13)	La1 ⁱⁱⁱ —Ni1—La1 ^{vi}	80.714 (18)

La1 ^{vii} —La1—La1 ^{viii}	72.91 (3)	La1 ^{iv} —Ni1—La1 ^{vi}	92.75 (2)
Ni1 ⁱ —La1—La1 ^{iv}	144.884 (9)	Ni1 ^{ix} —Ni1—La1 ^v	62.73 (2)
Ni1 ⁱⁱ —La1—La1 ^{iv}	98.17 (2)	Ni1 ^x —Ni1—La1 ^v	136.91 (4)
Ni1 ⁱⁱⁱ —La1—La1 ^{iv}	154.19 (4)	La1 ^{xi} —Ni1—La1 ^v	127.25 (4)
Ni1 ^{iv} —La1—La1 ^{iv}	53.37 (3)	La1 ^{xii} —Ni1—La1 ^v	75.73 (2)
Ni1 ^v —La1—La1 ^{iv}	93.94 (2)	La1 ⁱⁱⁱ —Ni1—La1 ^v	92.75 (2)
Ni1 ^{vi} —La1—La1 ^{iv}	103.58 (2)	La1 ^{iv} —Ni1—La1 ^v	80.714 (18)
Ni1—La1—La1 ^{iv}	50.410 (16)	La1 ^{vi} —Ni1—La1 ^v	152.44 (7)
La1 ^{vii} —La1—La1 ^{iv}	148.633 (12)	Ni1 ^{ix} —Ni1—La1	124.82 (6)
La1 ^{viii} —La1—La1 ^{iv}	99.864 (10)	Ni1 ^x —Ni1—La1	124.82 (6)
Ni1 ⁱ —La1—La1 ^v	98.17 (2)	La1 ^{xi} —Ni1—La1	138.87 (2)
Ni1 ⁱⁱ —La1—La1 ^v	144.884 (9)	La1 ^{xii} —Ni1—La1	138.87 (2)
Ni1 ⁱⁱⁱ —La1—La1 ^v	103.58 (2)	La1 ⁱⁱⁱ —Ni1—La1	76.22 (4)
Ni1 ^{iv} —La1—La1 ^v	93.94 (2)	La1 ^{iv} —Ni1—La1	76.22 (4)
Ni1 ^v —La1—La1 ^v	53.37 (3)	La1 ^{vi} —Ni1—La1	76.22 (4)
Ni1 ^{vi} —La1—La1 ^v	154.19 (4)	La1 ^v —Ni1—La1	76.22 (4)

Symmetry codes: (i) $x-1/2, y-1/2, z$; (ii) $x+1/2, y-1/2, z$; (iii) $-x-1/2, -y+1/2, -z$; (iv) $-x+1/2, -y+1/2, -z+1$; (v) $-x-1/2, -y+1/2, -z+1$; (vi) $-x+1/2, -y+1/2, -z$; (vii) $-x, -y, -z$; (viii) $-x, -y, -z+1$; (ix) $-x, -y+1, -z+1$; (x) $-x, -y+1, -z$; (xi) $x+1/2, y+1/2, z$; (xii) $x-1/2, y+1/2, z$.